AFB™ 6102B


Avery Dennison AFB™ 6102B is a black acrylic double coated foam tape with multipurpose acrylic adhesive on both sides. This firm yet thin foamed adhesive offers strong lamination properties and good weather and environmental resistance. An additional layer of adhesive offers resistance of migration toward plasticizer in vinyl substrates. Suitable for a wide range of applications, including nameplate, sign bonding, and control panel mounting.

FEATURES:

- · Foam tape with viscoelastic acrylic foam carrier
- · Closed cell structure
- Acrylic adhesive system
- Easy release paper liner

BENEFITS:

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- Good moisture, UV and high temperature resistance
- · Uniform bonding performance
- Can help eliminate the need for mechanical fasteners, drilling or grinding and related clean-up for certain applications



CONSTRUCTION:

Liner:

Polyethylene Coated White Paper

Adhesive:

Acrylic

Carrier:

Black Acrylic Foam Core

Adhesive:

Acrylic



AFB™ 6102B

2 mil PET

SS

12 in /min (305 mm / min)

72 hr dwell

| Adhesive Properties: | | i ypicai values | | | |
|----------------------|---------------|-----------------|------|---------------|--|
| Thickness | ASTM D-3652 | US Mils | MM's | Micron's (µm) | |
| Liner: | | 6.3 | 0.16 | 160 | |
| Carrier & Adhesive: | | 7.9 | 0.20 | 200 | |
| T | | 44.0 | 0.00 | 200 | |
| Total Caliper: | | 14.2 | 0.36 | 360 | |
| 1 | 305 mm / min) | | | | |
| Substrate | | Lbf / In | | N / 100 mm | |
| SS | 20 min dwell | 8.2 | | 144 | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |

10.5

Typical Values

184

| DYNAMIC SHEAR | Test Method(s): ASTM D-1002 | | | | |
|-----------------------------|-----------------------------|-----------------------|-----|--|--|
| 2 mil PET 0.5 in /min (12.7 | 7 mm / min) | | | | |
| Substrate | | Lbf / In ² | kPa | | |
| Liner | 72 hr dwell | 130.5 | 900 | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | <u>.</u> | | | | |
| NORMAL TENSILE | Test Method(s): ASTM D-897 | | | | |
| Aluminum 2 in / min (50.8 | mm / min) 1" sq (6.5 cm2) | | | | |
| ubstrate | | Lbf / In ² | kPa | | |
| Aluminum | 72 hr dwell | 129.1 | 890 | | |
| | | | | | |
| | | | | | |
| | | | | | |

| 2 mil PET 1" sq (6.5 cm2 | () 500 g | | | |
|------------------------------|----------|-------------|---------|--|
| Substrate | - | Min to Fail | | |
| SS | @ 90°C | > 10,000 | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| TEMPERATURES | | ° F | ° C | |
| Long Term Temp (10,000 mins) | | 194 ° F | 90 ° C | |
| Short Term Temp (240 mins) | | 302 ° F | 150 ° C | |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

STATIC SHEAR

. It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

Test Method(s): PSTC-101, ASTM D-3330

- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Tapes

Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

South America Rua Francisco Foga, 225 13280-000 Vinhedo SP Brazil

North America 250 Chester Street Painesville. Ohio

Phone: +55 19 3876 7736 Phone: +1 866-462-8379 Fax: +55 19 3876 7682 Fax: +1 888-358-4469