AFB™ 6111B


Avery Dennison AFB™ 6111B are black acrylic double coated foam tapes with a multipurpose acrylic adhesive on both sides. This conformable foam adhesive offers strong lamination properties and good weather and environmental resistance. An additional layer of adhesive offers resistance of migration toward plasticizer in vinyl substrates. Suitable for a wide range of applications, including large domestic appliances, nameplate or sign bonding, and control panel mounting.

FEATURES:

- · Foam tape with viscoelastic acrylic foam carrier
- · Closed cell structure
- · Acrylic adhesive system
- · Easy release polyethylene liner

BENEFITS:

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- Good moisture, UV and high temperature resistance
- · Uniform bonding performance
- Can help eliminate the need for mechanical fasteners, drilling or grinding and related clean-up for certain applications
- Polyethylene liner helps provide good moisture stability and easier converting with its high tear strength



CONSTRUCTION:

Liner:

Red Polyethylene Liner With Imprinted Avery Logo

Adhesive:

Acrylic

Carrier:

Black Acrylic Foam Core

Adhesive:

Acrylic

AFB™ 6111B

Adhesive Properties:

Thickness	ASTM D-3652	US Mils	MM's	Micron's (µm)	
Liner:		5.1	0.13	130	
Carrier & Adhesive:		43.3	1.10	1100	
Total Caliper:		48.4	1.23	1229	
DEEL ADVICTION	Total Mathe (A) DOTO 404	AOTAA D 0000			
PEEL ADHESION	Test Method(s): PSTC-101	, ASTM D-3330			
2 mil PET 90° 12 in /m Substrate	in (305 mm / min)	Lbf / In		N / 100 mm	
SS	20 min dwell	13.0		228	
33	20 min dweii	10.0		220	
2 mil PET 90° 12 in /m	in (305 mm / min)				
SS	72 hr dwell	17.0		298	
	<u> </u>				
DYNAMIC SHEAR	Test Method(s): ASTM D-1	002			
2 mil PET 0.5 in /min (12.	7 mm / min)				
Substrate		Lbf / In ²		kPa	
Lines	70	09.6		690	

DINAMIC SHEAR		rest iviethod(s). As rivi t	J-1002			
2 mil PET 0.5 in	/min (12.7 mm / min)					
Substrate				Lbf / In ²		kPa
Liner		72 hr dwell		98.6		680
NORMAL TENSILE		Test Method(s): ASTM [D-897			
Aluminum 2 in / i	min (50.8 mm / min)	1" sq (6.5 cm2)				
Substrate			•	Lbf / In ²	•	kPa
Aluminum		72 hr dwell		97.2		670

STATIC SHEAR	Test Method(s): PSTC-	101, ASTM D-3330	
2 mil PET 1" sq (6.5 cm2)	500 g		
Substrate		Min to Fail	
SS	@ 90°C	> 10,000	

TEMPERATURES	° F	° C
Long Term Temp (10,000 mins)	194 ° F	90 ° C
Short Term Temp (240 mins)	302 ° F	150 ° C
ener remp (2 to time)		

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- . It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Tapes

Typical Values