FM 2132


Avery Dennison FM 2132 is a 36 mil double coated white polyethylene foam with a high shear rubber adhesive. It bonds to a wide variety of low surface energy materials and features high shear strength and the ability to fill gaps. FM 2132 is commonly used in general industrial foam applications.

FEATURES:

- · Double coated tape construction
- · High shear rubber adhesive
- Polyethylene foam carrier
- · Super calendered kraft release liner

BENEFITS:

- Dimensional stability and good die cutting characteristics
- Strong bond to a wide variety of low surface energy materials
- High shear and high temperature resistance
- · Gap filling properties and good conformability
- High tensile strength and tear resistance with excellent die cutting performance



CONSTRUCTION:

Liner:

60# White Kraft

Adhesive:

Rubber

Carrier:

1/32" White Foam

Adhesive:

Rubber



FM 2132

Adhesive Properties:		Typical Values		
Thickness	ASTM D-3652	US mil	mm	micron (µm
Liner		3.5	0.09	90
Adhesive - Unwind		2.5	0.06	65
Carrier		31.0	0.79	785
Adhesive - Liner		2.5	0.06	65
Total Caliper without Liner:		36.0	0.91	915
Total Caliper:		39.5	1.00	1005
Total Caliper.		33.3	1.00	1000
PEEL ADHESION	Test Method(s): PSTC-101	, ASTM D-3330		
2 mil PET 72 hr dwell	180° 12 in /min (305 mm / min)			
Substrate		Lbf / In		N / Meter
SS	Liner	7.5		1,310
				10:0
	Unwind	7.5		1,310
				1.010
PP	Liner	7.5		1,310
	Unwind	7.5		1,310
LOOP TACK	Test Method(s): PSTC-16			
2 mil PET Initial 20 ir	n / min (508 mm / min)			
Substrate		Lbf / In		N / Meter
SS	Liner	12.0		2,100
STATIC SHEAR	Test Method(s): PSTC-107	, ASTM D 3654		
2 mil PET 72 hr dwell	1" sq (6.5 cm2) 1000 g			
Substrate	Mins to Fail			
SS	Liner	10,000		
	+	ļ		
TEMPERATURES		°F		° C
Minimum Application Towns and the		- F	1	10° C

APPLICATION TECHNIQUES

Minimum Application Temperature

Minimum Service Temperature

Maximum Service Temperature

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Fax: +86 512 57155059

50° F

-40° F

175° F

10° C

-40° C

80° C