
# FT 0900X

Avery Dennison FT 0900X is a 36 mil single coated black flock with a high performance low VOC acrylic adhesive. The adhesive bonds very well to low surface energy materials and the flock provides anti-squeak properties with high wear resistance. FT 0900X is commonly used in automotive applications and where low VOC properties are required.

#### **FEATURES:**

- Single coated tape construction
- Low outgassing high performance modified acrylic adhesive
- Nylon flock facestock
- Poly coated kraft release liner



## **BENEFITS:**

- Functional tape that allows for die cutting
- Solvent free adhesive with good adhesion to low surface energy materials
- Good heat resistance
- High abrasion resistance and NVH reduction
- Good moisture stability and lay flat properties

## **CONSTRUCTION:**

Liner:

82# Natural Poly Coated Kraft

Adhesive:

Low VOC Acrylic

**Carrier:** 

Flock



### FT 0900X

**Adhesive Properties:** 

| Thickness                    | ASTM D-3652               | US mil      | mm   | micron (µm) |
|------------------------------|---------------------------|-------------|------|-------------|
| Thickness                    | A311VI D-3032             |             |      |             |
| Liner                        |                           | 5.8         | 0.15 | 145         |
| Adhesive                     |                           | 4.8         | 0.12 | 120         |
| Carrier                      |                           | 31.0        | 0.79 | 785         |
| Total Caliper without Liner: |                           | 35.8        | 0.91 | 905         |
| Total Caliper:               |                           | 41.6        | 1.06 | 1050        |
| PEEL ADHESION                | Test Method(s): PSTC-101, | ASTM D-3330 |      |             |
|                              | 2 in /min (305 mm / min)  |             |      |             |
| Substrate                    | (555,                     | Lbf / In    |      | N / Meter   |
| SS                           |                           | 9.0         |      | 1,580       |
|                              |                           |             |      |             |
|                              |                           |             |      |             |
|                              |                           |             |      |             |
| ABS                          |                           | 10.0        |      | 1,750       |
|                              |                           |             |      |             |
|                              |                           |             |      |             |
|                              |                           | _           |      |             |
|                              |                           |             |      |             |
| +                            |                           |             |      |             |
|                              |                           |             |      |             |
| +                            |                           | +           |      |             |
| L                            |                           | _ <b>_</b>  | I    |             |

**Typical Values** 

| LOOP TACK | Test Method(s): PSTC-      | 16       |           |
|-----------|----------------------------|----------|-----------|
| 2 mil PET | 20 in / min (508 mm / min) |          |           |
| Substrate |                            | Lbf / In | N / Meter |
| SS        |                            | 3.5      | 610       |
|           |                            |          |           |
|           |                            |          |           |
|           |                            |          |           |
|           |                            |          |           |

| STATIC SH | EAR         | Test Method(s): PSTC-107, ASTM D 3654 |       |          |  |
|-----------|-------------|---------------------------------------|-------|----------|--|
| 2 mil PET | 72 hr dwell | 1" sq (6.5 cm2)                       | 500 g |          |  |
| Substrate |             | Mins to Fail                          |       |          |  |
| SS        |             |                                       |       | > 10,000 |  |
|           |             |                                       |       |          |  |
|           |             |                                       |       |          |  |
|           |             |                                       |       |          |  |
|           |             |                                       |       |          |  |

| TEMPERATURES                    | ° F    | 。 C    |
|---------------------------------|--------|--------|
| Minimum Application Temperature | 50° F  | 10° C  |
| Minimum Service Temperature     | -40° F | -40° C |
| Maximum Service Temperature     | 350° F | 175° C |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

## **APPLICATION TECHNIQUES**

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

## STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2018 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA

Phone: +1 866-462-8379 Fax: +1 888-358-4469