FT 7358


Fastape™ 7358 is manufactured with a differential removable acrylic and permanent rubber adhesive system. Designed for polishing pad applications

FEATURES:

- High tack rubber based adhesive
- Excellent removable acrylic adhesive providing good creep resistance and clean removability.

BENEFITS:

- · Easy release liner
- Improved die-cutting characteristics
- Matrix strippable
- Reinforces the polishing material



CONSTRUCTION:

Liner:

Glassine

Adhesive 1 Liner:

Removable Acrylic

Carrier:

Polyester

Adhesive 2 Uwind:

Permanent Rubber

FT 7358

Adhesive Properties:		Typical	Values
Thickness	Test Method(s): PSTC-133	US Mils	MM's
Liner:		3.2	0.08
Adhesive 1 Liner:		1.6	0.04
Carrier:		0.5	0.01
Adhesive 2 Uwind:		1.3	0.03
Total Caliper:		6.6	0.17

Total Caliper:		1.3		0.17	
		6.6			
i otai oanpori				<u> </u>	
PEEL ADHESION		Test Method(s): PST	C-101, ASTM D-3330, STD-10		
	2" min				
Substrate			Lbf / In	US Oz / In	N / Meter
SS	Liner	Initial	3.2	51	560
		1.60.1	0.7	100	11=0
	Unwind	Initial	6.7	107	1173
Painted Steel	Liner	Initial	3.9	62	683
		1.20.1	44.0	200	0504
	Unwind	Initial	14.3	229	2501
Polycarbonate	Liner	Initial	3.8	62	673
	11. 2. 1	Initial	15.0	240	2626
	Unwind	Initial	15.0	240	2020
PP	Liner	Initial	2.3	36	399
	I lavida al	Initial	13.0	209	2283
	Unwind	Initial	13.0	209	2203
LOOD TAOK		To a Marilla I/a) DOT	0.40.070.7		
LOOP TACK 2 mil PET 20" mir	2	Test Method(s): PST	U-16, STD-7		
Substrate	1		Lbf / In	US Oz / In	N / Meter
SS	Liner	Initial	3.1	49	540
	Unwind	Initial	10.3	166	1811
	<u> </u>		<u> </u>	!	1
STATIC SHEAR		Test Method(s): PST	C-107, ASTM D 3654, STD-9		
2 mil PET 1" sq (6.5	cm2) 1000 g				
Substrate	II. S	1-14-1	Min to Fail	1	
SS	Liner	Initial	> 1,000		
	Unwind	Initial	> 10,000		
	0	****			
TEMPERATURES			° F		° C
I LIMITERATURES			F0.0 F		10.0.0

Max Intermittent Operating Temp THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

50 ° F

131 ° F

158 ° F

APPLICATION TECHNIQUES

Max Continuous Operating Temp

Min Application Temp

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2013 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. Avery™ and all other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Fax: +86 512 57155059

Fax: +55 19 3876 7682

10 ° C

55 ° C

70 ° C