# FT A


Designed for bonding to a wide variety of plastic, metal and foam substrates where resistance to plasticizers and high temperatures is required.

# **FEATURES:**

- Polyester carrier
- Specially formulated acrylic adhesive
- Protected by a densified kraft release liner

#### **BENEFITS:**

- Excellent processing and die-cutting stability
- Elevated temperature, solvent and plasticizer resistance



## **CONSTRUCTION:**

Liner:

Densified Kraft

Adhesive 1 Liner:

Acrylic

Carrier:

Polyester

Adhesive 2 Uwind:

Acrylic



#### FT A

Adhesive Properties:		Typical Values		
Thickness	Test Method(s): PSTC-133	US Mils	MM's	Microns (μm)
Liner:		3.6	0.09	91
Carrier & Adhesives:		3.5	0.09	90
Total Caliper:		7.1	0.18	181

PEEL ADHESION		Test Method(s): PSTC-101, A	ASTM D-3330, STD-10		
2 mil PET 180° 12" i	min				
Substrate			Lbf / In	US Oz / In	N / Meter
SS	Liner	Initial	4.4	70	770
	Unwind	Initial	4.4	70	770
		·	·		· ·

LOOP TACK	Test Method(s): F	Test Method(s): PSTC-16, STD-7			
2 mil PET 180°	20" min				
Substrate		Lbf / In	US Oz / In	N / Meter	
SS	Liner	4.4	70	770	
	Unwind	4.4	70	770	
		·			

STATIC SHEAR	Test Method(s): PSTC-107, ASTM D 3654, STD-9			
2 mil PET 1" sq (6.5 cm2)	5.5 lbs (2.5 kg)			
Substrate		Min to Fail		
SS	Liner	> 500		
	Unwind	> 500		

TEMPERATURES	۰F	° C
Min Application Temp	50 ° F	10 ° C
Max Continuous Operating Temp	200 ° F	93 ° C
Max Continuous Operating Temp	250 ° F	121 ° C
Max Cont OpTemp w/ Heat Lam		

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

#### **APPLICATION TECHNIQUES**

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

### STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.

Europe

Tieblokkenlaan 1



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Fax: +86 512 57155059

B-2300 Turnhout Belaium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 Phone: +86 512 57155001

South America Rua Francisco Foga, 225 250 Chester Street 13280-000 Vinhedo SP Brazil

North America Painesville, Ohio 44077 USA

Fax: +55 19 3876 7682

Phone: +55 19 3876 7736 Phone: +1 866-462-8379 Fax: +1 888-358-4469