




# FT Y1092

# FEATURES:

- Highly engineered acrylic adhesive
- Uniform adhesive thickness
- Easy release liner

# **BENEFITS**:

- Excellent resistance to solvents, chemicals, plasticizes, moisture, temperature and UV-light
- Consistent application performance
- · Good conformability to flat or curved surfaces
- High degree of transparency
- Facilitates easy removal at point of application



Liner: Yellow Glassine Adhesive: Acrylic

**CONSTRUCTION:** 



dhesive Properties:		Typical Values		
Thickness	Test Method(s): PSTC-133	US Mils		MM's
_iner:		3.0		0.07
Adhesive:		0.9		0.02
Fotal Caliper:		3.9		0.10
PEEL ADHESION	Test Method(s): PSTC-101, ASTM	1 D-3330 STD-10		
2 mil PET 180° 12" min	Test Method(s). 1 510-101, ASTA	10-3330, 310-10		
Substrate		Lbf / In	US Oz / In	N / Meter
SS	20 min dwell	2.3	36	399
	24 hr dwell	2.4	38	420
		1.0	20	329
Polycarbonate	20 min dwell	1.9	30	329
	24 hr dwell	2.2	35	380
		£+£		300
Painted Steel	20 min dwell	2.0	32	350
		2.2	35	380
	24 hr dwell	2.2	30	360
Polypropylene	20 min dwell	0.9	15	159
	24 hr dwell	1.1	17	189
		1.1		100
LOOP TACK	Test Method(s): PSTC-16, STD-7			
2 mil PET 180° 20" / min				
Substrate		Lbf / In	US Oz / In	N / Meter
SS	Initial	3.2	52	566
STATIC SHEAR	Test Method(s): PSTC-107, ASTN	1 D 3654, STD-9		
2 mil PET 1" sq (6.5 cm2) 2500	) g	Min to Fail		
Substrate	Initial	Min to Fail > 2,500	1	
SS	11 IIIIdi	> 2,000		
TEMPERATURES		° F	•	° C
Min Application Temp Max Continuous Operating Temp		50 ° F 248 ° F		10 ° C 120 ° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

### **APPLICATION TECHNIQUES**

• It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

. Bond strength is dependent upon the amount of adhesive-to-surface contact developed

· Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

### **STORAGE / SHELF LIFE**

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2013 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. Avery™ and all other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China. 215335 Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

South America Rua Francisco Foga, 225 250 Chester Street 13280-000 Vinhedo SP Brazil Phone: +55 19 3876 7736 Phone: +1 866-462-8379

North America Painesville, Ohio 44077 USA Fax: +55 19 3876 7682 Fax: +1 888-358-4469