



# FT 2055


Avery Dennison FT 2055 is a dispersion-based modified acrylic transfer tape used for bonding polyurethane foam, polyester fibers, felts and fabrics to a wide variety of substrates. Provides high adhesion to medium and low surface energy materials such as PP, PE, TPO, ABS, PVC, polystyrene and painted metals. Ideal for general purpose foam bonding applications such as gaskets, sound deadening and insulation materials in automotive, building and construction, appliance assembly and general industrial sub-assembly.

## **FEATURES:**

- Dispersion-based modified acrylic adhesive
- APEO free adhesive
- High initial tack
- Easy release OPP film liner
- Broad range of service temperatures

## **BENEFITS**:

- Excellent resistance to solvents, chemicals,
- plasticizers, temperature and UV light
- Medium resistance to moisture
- Good conformability to flat or curved surfaces
- Immediate initial adhesion for part placement
- Excellent water jet and die cutting characteristics



## **CONSTRUCTION:**

Liner: White OPP film liner

#### ve Adhesive:

Dispersion-based modified acrylic



### FT 2055

112000				
Adhesive Properties		Typical Values		
THICKNESS	US Mils	mm	Microns (µm)	
Adhesive	1.97	0.050	50	
Liner	2.36	0.060	60	
Total	4.33	0.110	110	
*PSTC-133				
PEEL ADHESION				
2 mil PET; 180°; 12" / min				
Substrate	Lbf / in	N / Meter		
	72 hr		72 hr	
Stainless steel	6.28	6.28 1100		
ABS	5.71	1000		
Polypropylene	5.14	5.14		
*PSTC-101, ASTM D-3330, STD-10	L			
LOOP TACK				
2 mil PET; 90°; 20" / min; 1" sq (6.5 cm <sup>2</sup> )				
Substrate	Lbf / in		N / Meter	
Stainless steel	5.14		900	
Finat tack	5.14		900	
*PSTC-16, STD-7	·	•		
TEMPERATURES				
Min. Application Temp.	50°F		10°C	
Min. Service Temp.	-40°F		-40°C	
Max. Service Temp.	310°F		155°C	
*TEST METHODS		•		

Note: The listed values are typical only and not intended to serve as product specifications

#### **APPLICATION TECHNIQUES**

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- · Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

## STORAGE AND SHELF LIFE

The shelf life of the product is one year when stored at 18-22°C / 64-72°F, 30-70% relative humidity and out of direct sunlight, in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific Kunshan, China NO. 618 Nanhe Road Kunshan Economic & Performance Technological Zone China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059

Tapes

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 Europe Bld J.F. Kennedy 1 7060 Soignies Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469