# FT 7329X


Avery Dennison FT 7329X is a 3.7 mil double coated polyester with a low VOC modified acrylic adhesive. It bonds well to low surface energy materials and has excellent foam bonding properties. FT 7329X is commonly used for general industrial foam bonding and where low VOC properties are required.

## **FEATURES:**

- · Double coated tape construction
- · Low outgassing modified acrylic adhesive
- · Polyester film carrier
- · Glassine paper release liner

## **BENEFITS:**

- Dimensional stability and good die cutting characteristics
- Solvent free adhesive with excellent foam bonding performance
- High tensile strength and good converting performance
- Dimensional stability and excellent water jet and die cutting performance



## **CONSTRUCTION:**

Liner:

Havana Glassine

Adhesive:

Low VOC Acrylic

Carrier:

Polyester

Adhesive:

Low VOC Acrylic



#### FT 7329X

Adhesive Properties:			Typical Values		
Thickness	ASTM D-3652	US mil	mm	micron (µm)	
Liner		2.7	0.07	70	
Adhesive - Unwind		1.3	0.03	35	
Carrier		0.5	0.01	15	
Adhesive - Liner		1.9	0.05	50	
Total Caliper without Liner:		3.7	0.09	100	
Total Caliper:		6.4	0.16	170	
PEEL ADHESION	Test Method(s): PSTC-101	, ASTM D-3330			
2 mil PET 72 hr dwell	180° 12 in /min (305 mm / min)				
Substrate		Lbf / In	,	N / Meter	
SS	Liner	8.0		1,400	
	Unwind	7.0	1,230		
400	Linear	5.0	880		
ABS	Liner	5.0		880	
	Unwind	4.5		790	
	•		<u> </u>		
LOOP TACK	Test Method(s): PSTC-16				
2 mil PET Initial 20 in	/ min (508 mm / min)				
Substrate		Lbf / In		N / Meter	
SS	Liner	3.5		610	
	1	-			
STATIC SHEAR 2 mil PET 72 hr dwell	Test Method(s): PSTC-107 1" sq (6.5 cm2) 500 g	, ASTM D 3654			
Substrate	1 04 (0.0 01112) 000 g	Mins to Fail			
SS	Liner	10,000			
	EITO	,			

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

# **APPLICATION TECHNIQUES**

Minimum Application Temperature

Minimum Service Temperature

Maximum Service Temperature

**TEMPERATURES** 

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

#### STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific
Kunshan, China,
NO. 618 Nanhe Road
Performance
Tapes
Kunshan Economic &
Technological Zone
China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

50° F

-40° F

250° F

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA

° C

10° C

-40° C

120° C

Phone: +1 866-462-8379 Fax: +1 888-358-4469