FASSON® 955


Designed to provide the surface of a foil tape and the easy application of a cloth tape for use on duct work.

FEATURES:

- Aggressive rubber based adhesive
- Metalized polycoated cloth

BENEFITS:

- Aggressive tack and adhesion
- Airtight, moisture-free seal
- Tested in accordance with UL 723



CONSTRUCTION:

Carrier:

Metalized Poly-coated Cloth

Adhesive:

Rubber

FASSON® 955

Adhesive Properties:		Typical Values		
Thickness	Test Method(s): PSTC-133	US Mils	MM's	Microns (μm)
		0.4	0.05	50
Adhesive:		2.1	0.05	53
Carrier:		10.4	0.26	264
Fotal Caliper:		12.5	0.32	317
Total Caliper.		12.5	0.32	317
PEEL ADHESION	Test Method(s): PSTC-101, ASTI	M D-3330, STD-10		
Product 180º 12" min Substrate		Lbf / In	US Oz / In	N / Meter
SS S	Initial	3.0	48	525
,0	THIGH	0.0	10	020
	,			
Product	Test Method(s): PSTC-131, ASTI	M D-882, STD-3A,B,C		
Product Substrate		Lbf / In	US Oz / In	N / Meter
Product	I	1.6	26	280
TOUUGE		1.0	20	200
ELONGATION	Test Method(s): PSTC-131, ASTI	M D-882, STD-3A,B,C		
Product				
Substrate		%		
Product		14.0		
			<u> </u>	
STATIC SHEAR	Test Method(s): PSTC-107, ASTI	M D 3654, STD-9		
	(1.0 kg)			
Substrate		Min to Fail		
SS		> 15		
	-			
STATIC SHEAR	Test Method(s): PSTC-107, ASTI	M D 3654, STD-9		
Product 1" sq (6.5 cm2) 5.5 Substrate	lb (2.5 kg)	Min to Fail		
SS	Initial	> 50		
	IIIIIai	> 50		
TEMPERATURES		° F		° C
Min Application Temp		•		_
Max Continuous Operating Temp				
Max Intermittent Operating Temp			İ	

Max Intermittent Operating Temp THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance

Asia Pacific Kunshan, China. NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio

Phone: +1 866-462-8379 Fax: +1 888-358-4469