



FM M2713 Clearback

FM M2713 Clearback is part of a pressure-sensitive fastening system consisting of a variety of cross linked, closed-cell, polyethylene foams in various thicknesses, densities and colors, and coated both sides with specifically formulated pressure-sensitive adhesives.

CONSTRUCTION & TYPICAL APPLICATION:

- Consists of a 2 mm black, cross-linked, closed-cell, polyethylene foam coated on both sides with an acrylic adhesive. It offers very high adhesion and cohesive properties.
- Produced in self-wound format on a clear siliconized PET 50µ.
- Foam tape with exceptional resistance to ageing, weathering, solvents. Recommended when a thicker foam is a must.



| Adhesion with Substrates | | | |
|--------------------------|--------|------------------|--------|
| Metal / Aluminium | High | Acrylic / PET | Medium |
| Glass / Ceramics | High | Polystyrene | Medium |
| Painted Surface | Medium | PP / PE / PS | Medium |
| Wood / Board / Paper | Medium | Textile / Cotton | Medium |
| Soft PVC | Medium | Rubber / EPDM | Medium |
| Rigid PVC | Medium | Smooth Substrate | High |
| PC / ABS | High | Rough Substrate | Medium |

RESISTANCE:

• Resistant to water, detergents, alcohol. Not recommended for use in contact with aliphatic and some aromatic solvents.

SHELF LIFE:

• 2 years when stored at $15/25^{\circ}$ C and \pm 50% relative humidity.



FM M2713 CLEARBACK

| ADHESIVE DATA | Typical Values* | Test Method |
|--|-----------------|-------------|
| Peel 180° (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4) - after 20 minutes | > 20** | FTM 1 |
| Shear on brushed stainless steel (ref. Nokoro 304 poli. N°4) 1kg – 25mm x 25mm (hours) | > 1000 | FTM 8 |

| CARRIER DATA | Typical Values* | Test Method |
|--------------------------|------------------|-------------|
| Tensile (N/15mm) | MD 27 CD 17,5 | DIN 53455 |
| Elongation (%) (max.) | MD 400 CD 400 | DIN 53455 |
| Density | Medium | |

| TEMPERATURE RESISTANCE | Typical Values* | Test Method |
|---------------------------------|------------------|-------------|
| Minimum Application Temperature | + 10°C | |
| End-use Temperature Range | - 40°C to + 95°C | |

| RELEASE LINER | Typical Values* | Test Method |
|---------------|-----------------|-------------|
| Clear PET | 50µ | ISO 536 |

| THICKNESS | Typical Values* | Test Method |
|--------------------|-----------------|-------------|
| Carrier + Adhesive | 2,1mm | ISO 534 |

^{*}Values given are typical and are not necessarily for use in specifications.

APPLICATION TECHNIQUES:

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

IMPORTANT NOTICE:

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison Conditions of Sales, a copy of which is available upon request.

lease refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation.

All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation



Performance

Asia Pacific

Kunshan, China, No. 618 Nanhe Road Kunshan Economic & Technological Zone China 215335 Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1

B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

Bld J.F. Kennedy 1 7060 Soignies Belgium Phone: +32 (0)14 404 963 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA

Phone: +1 866-462-8379 Fax: +1 888-358-4469

^{**}Foam cleavage.