



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 8327**  
 SUPPORT: **PE FOAM**  
 SUBSTRATE: **SS**  
 CERT NO.: **230103 - 0826**



**AISIN AESK1701**  
 OEM Rev Date: Jan 14  
 Aisin Engineering Standard

**TEST PARAMETERS:**

**INITIAL PERFORMANCE**

SECTION: **4.2.3 A) Initial Performance**

**Condition**

A) Initial, 15 mins @ RT

**Specification**

**2.9 N / 15 mm**

**Results**

14.23

**Status**

**Pass**

SECTION: **4.2.3 B) Initial Adhesive Force**

**Condition**

B) Initial, 3 sec @ 10 g

**Specification**

**29 kPa**

**Results**

90.4

**Status**

**Pass**

SECTION: **4.2.3 C) Anchor Force**

**Condition**

C) Initial, 90° Inverted Under 50 g Load from SS

**Specification**

**> 5 < 60 minutes**

**Results**

> 90

**Status**

**Reported**

C) Initial, 90° Inverted Under 50 g Load from Aluminum

**> 5 < 60 minutes**

> 90

**Reported**

SECTION: **4.2.3 D) Cohesive Force**

**Condition**

D) Cohesion, 24 hrs @ RT

**Specification**

**< 10 mm lift**

**Results**

No Lifting

**Status**

**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.