



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 0900X**
 SUPPORT: **FLOCK**
 SUBSTRATE: **ABS**
 CERT NO.: **231128 - 1341**

ASTM D1000
 OEM Rev Date: 41274



TAPE REQUIREMENTS:

SECTION : **Peel Adhesion - ABS**
 Initial, 20 mins @ RT

ASTM D1000

Specification
4 N / cm

Results
 15.2

Status
Pass

High Temp, 7 days @ 82°C

11.6 N / cm

15.7

Pass

Cycles (5X)

4 hrs @ 70°C
 4 hrs @ 38°C / 95-100% RH
 16 hrs @ -29C

11.6 N / cm

15.0

Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.