



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 8392**  
 SUPPORT: **PEU FOAM**  
 SUBSTRATE: **ABS**  
 CERT NO.: **230103 - 0828**



**CHRYSLER MS-AY-301-B2**  
 OEM Rev Date : Apr 03  
 Cellular Polyurethane - Low Density  
 Cellular Polyurethane with High Temp PSA  
 Type 2 - Table 3

**TEST PARAMETERS:**

**Requirements for a Room Temp PSA**

SECTION: <b>3.3.2 Adhesion Test</b>	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.1, Adhesion Test, Initial, Room Temp		<b>274 N / m</b>	1419.7	<b>Pass</b>

SECTION: <b>3.3.2 Adhesion Test</b>	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Adhesion Test, 2.2, Heat Aged, 168 hrs @ 60°C		<b>330 N / m</b>	2826.5	<b>Pass</b>

SECTION: <b>3.3.2 Adhesion Test</b>		<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.3, Adhesion Test, After Thermo-Cycling Cycles, 2x Table 3 79°C 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -30°C Repeat twice then 168 hrs @ 79°C		<b>No Loss of Adhesion or Detrimental Effect</b>	Good, Stable No Lifting	<b>Pass</b>

SECTION: <b>3.3.2 Adhesion Test</b>		<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.4, Adhesion Test, Heat Resistance, 8 hrs @ 79°C		<b>No Shrinkage, Loss of Adhesion or Detrimental Effect</b>	Good, No Adhesion Loss or Lift	<b>Pass</b>

CERTIFIED BY:

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.