



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8327
SUPPORT: EPDM FOAM
SUBSTRATE: 10% TALC PP
CERT NO.: 240119 - 0641



CHRYSLER MS-AY301 C1
OEM Rev Date : Apr 03
Cellular Polyurethane - Low Density
Cellular Polyurethane with Backing and Room Temp PSA
Type 1 - Table 2

TEST PARAMETERS:


Requirements for a Room Temp PSA

SECTION: 3.3.2 Adhesion Test	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.1, Adhesion Test, Initial, Room Temp		274 N / m	446.6	Pass

SECTION: 3.3.2 Adhesion Test	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Adhesion Test, 2.2, Heat Aged, 168 hrs @ 60°C		330 N / m	961.4	Pass

SECTION: 3.3.2 Adhesion Test		<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.3, Adhesion Test, After Thermo-Cycling Cycles, 2x Table 2 70°C 24 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -30°C Repeat twice then 168 hrs @ 70°C		No Loss of Adhesion or Detrimental Effect	Good, Stable No Lifting	Pass

SECTION: 3.3.2 Adhesion Test		<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.4, Adhesion Test, Heat Resistance, 8 hrs @ 70°C		No Shrinkage, Loss of Adhesion or Detrimental Effect	Good, No Adhesion Loss or Lift	Pass

CERTIFIED BY: 
David Nichols II, Automotive Lab Technician

ISSUE DATE: **1-1-24**

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.