



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBA 8960
SUPPORT: 2.5 MM EPDM FOAM
SUBSTRATE: PP
CERT NO.: 240119 - 0646

CHRYSLER MS-AY-430 B
OEM Rev Date: May 11
Die-Cut Ethylene Propylene Diene Monomer (EPDM) Closed Cell Rubber
Type 2
B - Cellular EPDM with PSA

TEST PARAMETERS:

SECTION: 5.0 Adhesion

Specification: No Adhesion Loss or Separation

Adhesion, Environment Cycling, Cycles (2X)

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Results Status
Good, Stable, no Lifting Pass

SECTION: 5.0 Adhesion Test

ASTM D903-98 10

Specification: 274

N / m

Adhesion Test, 20 mins @ RT

Results Status
423.2 Pass

CERTIFIED BY:

[Signature]

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.