



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1123
SUPPORT: EVA FOAM
SUBSTRATE: PP
CERT NO.: 230103 - 0830



CHRYSLER MS-AY-518-B1
OEM Rev Date: Oct 10
Ethylene Vinyl Acetate (EVA) - Cellular - Water and Dust Seals

TAPE REQUIREMENTS:
Table 2 Physical Properties of Adhesive Systems

TEST: 1. Initial ASTM D903-98 10 Specification 274 N / m Results 284.9 Status Pass

TEST: 2. Extended Term Heat Aging \* ASTM D573 -08 \* Specification 330 N / m Results 408.6 Status Pass

TEST: 3. Thermo Cycling 4.3.1 Specification No Shrink, Loss of Adhesion or Detrimental Effect Results No Lifting, Shrink or Loss of Adhesion Status Pass

TEST: 4. Short Term Heat Aging ASTM D573 -08 \* Specification No Shrink, Loss of Adhesion or Detrimental Effect Results No Lifting, Shrink or Loss of Adhesion Status Pass

TEST: 8. Burn Rate FMVSS 302 09 Specification 100 mm / min Results Not on Part Model Status Not Tested

CERTIFIED BY:

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked \*.

