

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.: **FT 1126 12 PT BD** EPDM FOAM E-COATED METAL 230103 - 0837



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 Heat Aging Shrink ASTM D3575-08* Specification: < 5% Substrate Results Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width Pass ABS Specification: < 5% **Results** Status **Substrate** Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C PP Pass Specification: Substrate **Results** < 5% Status 2.1, Heat Aging, 30 mins @ 100° C **E-COATED METAL** Stable, Less than 5% Length and Width Pass SECTION: 2.2 Adhesion Specification: No Adhesion Loss or Delamiantion 2.2, Adhesion, Cycles (2X) Substrate Results Status Good, Stable, no Lifting 72 hrs @ 70° C ABS Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C Specification: **No Adhesion Loss or Delamiantion** 2.2, Adhesion, Cycles (2X) Substrate Results Status Good, Stable, no Lifting 72 hrs @ 70° C PP Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C Specification: No Adhesion Loss or Delamiantion 2.2, Adhesion, Cycles (2X) Substrate Results Status 72 hrs @ 70° C **E-COATED METAL** Good, Stable, no Lifting Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C

CERTIFIED BY:

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: