

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FT 1158 **EPDM FOAM** ABS 230105 - 1158



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material Cellular PVN with PSA

TEST PARAMETERS: SECTION: 21 Heat Aging

SECTION: 2.1 Heat Aging	Shrink ASTM D3575	-08*	
Specification: <5% 2.1, Heat Aging, 30 mins @ 100° C	<u>Substrate</u> ABS	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate PP	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate E-COATED METAL	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
SECTION: 2.2 Adhesion			
Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> ABS	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Los	s or Delamiantion		
2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	Substrate PP	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
	s or Delamiantion	Populto	Status
2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	Substrate E-COATED METAL	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

> Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: 5-30-2002

Page 1 of 1