

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FT 1158 NITRILE VINYL FOAM PP 230105 - 1158



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material Cellular PVN with PSA

TEST PARAMETERS:

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

| SECTION: 2.1 Heat Aging Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C | Shrink ASTM D3575- Substrate ABS | ^{.08*} Results Stable, Less than 5% Length and Width | <u>Status</u> Pass |
|--|---|--|-----------------------|
| Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C | <u>Substrate</u> PP | <u>Results</u> Stable, Less than 5% Length and Width | <u>Status</u> Pass |
| Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C | Substrate E-COATED METAL | <u>Results</u> Stable, Less than 5% Length and Width | <u>Status</u> Pass |
| SECTION: 2.2 Adhesion Specification: No Adhesion Loss 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C | s or Delamiantion <u>Substrate</u> ABS | <u>Results</u> Good, Stable, no Lifting | <u>Status</u> Pass |
| Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C | s or Delamiantion <u>Substrate</u> PP | <u>Results</u> Good, Stable, no Lifting | <u>Status</u> Pass |
| Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C | s or Delamiantion <u>Substrate</u> E-COATED METAL | <u>Results</u> Good, Stable, no Lifting | <u>Status</u> Pass |

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

5-30-2002 Page 1 of 1