

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

TEST REPORT

PRODUCT: **HPA 1905**

SUPPORT: NITRILE VINYL FOAM

SUBSTRATE: ABS

CERT NO.: 230103 - 0838



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

TEST PARAMETERS:

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

SECTION: 2.1 Heat Aging Shrink ASTM D3575-08*

Specification: <5% Substrate Results Status
2.1, Heat Aging, 30 mins @ 100° C ABS Stable, Less than 5% Length and Width Pass

Specification: < 5% Substrate Results Status

2.1, Heat Aging, 30 mins @ 100° C PP Stable, Less than 5% Length and Width Pass

Specification: < 5% Substrate Results
2.1, Heat Aging, 30 mins @ 100° C E-COATED METAL Stable, Less than 5% Length and Width Pass

Specification: <5% Substrate Results Status
2.1, Heat Aging, 30 mins @ 100° C SS Stable, Less than 5% Length and Width Pass

SECTION: 2.2 Adhesion

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X)

72 hrs @ 70° C

Substrate

ABS

Good, Stable, no Lifting

Pass

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X)

72 hrs @ 70° C

PP

Substrate
PP

Good, Stable, no Lifting
Pass

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Substrate Results Good, Stable, no Lifting Pass

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Cycles (2X)

72 hrs @ 70° C

Substrate
SS

Good, Stable, no Lifting
Pass

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

ISSUE DATE: 1-1-24

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.