

**TEST REPORT** 

**HPA 1905 PET** SUPPORT: NITRILE VINYL FOAM

SUBSTRATE: **ABS** 

PRODUCT:

230103 - 0839 CERT NO.:



Painesville, Ohio 44077 Phone:

866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

250 Chester Street

email: psa.tape@averydennison.com

URL: tapes.averydennison.com **CHRYSLER MS-AY-522 B TYPE 1** 

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

**TEST PARAMETERS:** 

SECTION: 2.1 **Heat Aging** Shrink ASTM D3575-08\*

> Specification: **Substrate** Results Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass**

> Specification: < 5% **Substrate Results Status**

> 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass**

> Substrate Specification: < 5% Results **Status** Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **E-COATED METAL Pass**

> Specification: **Substrate Results** < 5% Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width SS **Pass**

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

Results 2.2, Adhesion, Cycles (2X) Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **ABS Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion** 

**Substrate** 2.2, Adhesion, Cycles (2X) Results **Status** 72 hrs @ 70° C E-COATED METAL Good, Stable, no Lifting **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Cycles (2X) Substrate Results <u>Status</u> 72 hrs @ 70° C Good, Stable, no Lifting **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

**CERTIFIED BY:** 

1-1-24 ISSUE DATE:

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.