



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8217
 SUPPORT: EPDM FOAM
 SUBSTRATE: ABS
 CERT NO.: 230103 - 0839



CHRYSLER MS-AY-522 B TYPE 1
 OEM Rev Date: Jul 06
 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
 Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1	Heat Aging	Shrink	ASTM D3575-08*		
Specification:	< 5%			Substrate	Results
2.1, Heat Aging, 30 mins @ 100° C				ABS	Stable, Less than 5% Length and Width
					Status
					Pass
Specification:	< 5%			Substrate	Results
2.1, Heat Aging, 30 mins @ 100° C				PP	Stable, Less than 5% Length and Width
					Status
					Pass
Specification:	< 5%			Substrate	Results
2.1, Heat Aging, 30 mins @ 100° C				E-COATED METAL	Stable, Less than 5% Length and Width
					Status
					Pass
SECTION: 2.2	Adhesion				
Specification:	No Adhesion Loss or Delamination			Substrate	Results
2.2, Adhesion, Cycles (2X)				ABS	Good, Stable, no Lifting
72 hrs @ 70° C					
24 hrs @ 38° C / 95% RH					
72 hrs @ -40° C					
					Status
					Pass
Specification:	No Adhesion Loss or Delamination			Substrate	Results
2.2, Adhesion, Cycles (2X)				PP	Good, Stable, no Lifting
72 hrs @ 70° C					
24 hrs @ 38° C / 95% RH					
72 hrs @ -40° C					
					Status
					Pass
Specification:	No Adhesion Loss or Delamination			Substrate	Results
2.2, Adhesion, Cycles (2X)				E-COATED METAL	Good, Stable, no Lifting
72 hrs @ 70° C					
24 hrs @ 38° C / 95% RH					
72 hrs @ -40° C					
					Status
					Pass

CERTIFIED BY:

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.