



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 8217  
SUPPORT: EPDM FOAM  
SUBSTRATE: PP  
CERT NO.: 230103 - 0839



**CHRYSLER MS-AY-522 B TYPE 1**  
OEM Rev Date: Jul 06  
Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material  
Cellular PVN with PSA

**TEST PARAMETERS:**

SECTION: <b>2.1</b>	<b>Heat Aging</b>	Shrink	ASTM D3575-08*		
	Specification: <b>&lt; 5%</b>			<b>Substrate</b>	<b>Results</b>
	2.1, Heat Aging, 30 mins @ 100° C			ABS	Stable, Less than 5% Length and Width
					<b>Status</b>
					Pass
	Specification: <b>&lt; 5%</b>			<b>Substrate</b>	<b>Results</b>
	2.1, Heat Aging, 30 mins @ 100° C			PP	Stable, Less than 5% Length and Width
					<b>Status</b>
					Pass
	Specification: <b>&lt; 5%</b>			<b>Substrate</b>	<b>Results</b>
	2.1, Heat Aging, 30 mins @ 100° C			E-COATED METAL	Stable, Less than 5% Length and Width
					<b>Status</b>
					Pass
SECTION: <b>2.2</b>	<b>Adhesion</b>				
	Specification: <b>No Adhesion Loss or Delamination</b>			<b>Substrate</b>	<b>Results</b>
	2.2, Adhesion, Cycles (2X)			ABS	Good, Stable, no Lifting
	72 hrs @ 70° C				
	24 hrs @ 38° C / 95% RH				
	72 hrs @ -40° C				
					<b>Status</b>
					Pass
	Specification: <b>No Adhesion Loss or Delamination</b>			<b>Substrate</b>	<b>Results</b>
	2.2, Adhesion, Cycles (2X)			PP	Good, Stable, no Lifting
	72 hrs @ 70° C				
	24 hrs @ 38° C / 95% RH				
	72 hrs @ -40° C				
					<b>Status</b>
					Pass
	Specification: <b>No Adhesion Loss or Delamination</b>			<b>Substrate</b>	<b>Results</b>
	2.2, Adhesion, Cycles (2X)			E-COATED METAL	Good, Stable, no Lifting
	72 hrs @ 70° C				
	24 hrs @ 38° C / 95% RH				
	72 hrs @ -40° C				
					<b>Status</b>
					Pass

CERTIFIED BY:

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.  
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.  
This laboratory is not accredited for the calibrations or tests marked \*.