



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT


PRODUCT: FT 8302
 SUPPORT: EPDM FOAM
 SUBSTRATE: ABS
 CERT NO.: 230103 - 0840



CHRYSLER MS-AY-522 B TYPE 1
 OEM Rev Date: Jul 06
 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
 Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 Heat Aging	Shrink	ASTM D3575-08*		
Specification: < 5%	Substrate		Results	Status
2.1, Heat Aging, 30 mins @ 100° C	ABS		Stable, Less than 5% Length and Width	Pass
Specification: < 5%	Substrate		Results	Status
2.1, Heat Aging, 30 mins @ 100° C	PP		Stable, Less than 5% Length and Width	Pass
Specification: < 5%	Substrate		Results	Status
2.1, Heat Aging, 30 mins @ 100° C	E-COATED METAL		Stable, Less than 5% Length and Width	Pass
Specification: < 5%	Substrate		Results	Status
2.1, Heat Aging, 30 mins @ 100° C	SS		Stable, Less than 5% Length and Width	Pass
SECTION: 2.2 Adhesion				
Specification: No Adhesion Loss or Delamination	Substrate		Results	Status
2.2, Adhesion, Cycles (2X)	ABS		Good, Stable, no Lifting	Pass
72 hrs @ 70° C				
24 hrs @ 38° C / 95% RH				
72 hrs @ -40° C				
Specification: No Adhesion Loss or Delamination	Substrate		Results	Status
2.2, Adhesion, Cycles (2X)	PP		Good, Stable, no Lifting	Pass
72 hrs @ 70° C				
24 hrs @ 38° C / 95% RH				
72 hrs @ -40° C				
Specification: No Adhesion Loss or Delamination	Substrate		Results	Status
2.2, Adhesion, Cycles (2X)	E-COATED METAL		Good, Stable, no Lifting	Pass
72 hrs @ 70° C				
24 hrs @ 38° C / 95% RH				
72 hrs @ -40° C				
Specification: No Adhesion Loss or Delamination	Substrate		Results	Status
2.2, , Cycles (2X)	SS		Good, Stable, no Lifting	Pass
72 hrs @ 70° C				
24 hrs @ 38° C / 95% RH				
72 hrs @ -40° C				

CERTIFIED BY: 

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.