

**TEST PARAMETERS:** 

 250 Chester Street

 Painesville, Ohio 44077

 Phone:
 866-GO-AVERY (866-462-8379)

 Fax:
 888-358-4469

 email:
 psa.tape@averydennison.com

 URL:
 tapes.averydennison.com

## **TEST REPORT**

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.: FT 8302 EPDM FOAM SS 230103 - 0840



## CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material Cellular PVN with PSA

SECTION: 2.1 Heat Aging Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Shrink ASTM D3575- Substrate ABS	<sup>.08∗</sup> <u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate PP	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate E-COATED METAL	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
SECTION: 2.2 Adhesion Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> ABS	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> PP	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> E-COATED METAL	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification:         No Adhesion Los           2.2, , Cycles (2X)         72 hrs @ 70° C           24 hrs @ 38° C / 95% RH         72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> SS	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass

CERTIFIED BY:

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

5-1-2005 Page 1 of 1