



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8302
 SUPPORT: PET FOAM
 SUBSTRATE: E-COATED METAL
 CERT NO.: 230103 - 0841



CHRYSLER MS-AY-522 B TYPE 1
 OEM Rev Date: Jul 06
 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
 Cellular PVN with PSA

TEST PARAMETERS:

SECTION:	TEST	Shrink	ASTM D3575-08*	Substrate	Results	Status
2.1	Heat Aging	Specification: < 5%		ABS	Stable, Less than 5% Length and Width	Pass
	2.1, Heat Aging, 30 mins @ 100° C					
	Specification: < 5%			PP	Stable, Less than 5% Length and Width	Pass
	2.1, Heat Aging, 30 mins @ 100° C					
	Specification: < 5%			E-COATED METAL	Stable, Less than 5% Length and Width	Pass
	2.1, Heat Aging, 30 mins @ 100° C					
	Specification: < 5%			SS	Stable, Less than 5% Length and Width	Pass
	2.1, Heat Aging, 30 mins @ 100° C					

SECTION:	2.2	Adhesion	Specification: No Adhesion Loss or Delamination			
	2.2, Adhesion, Cycles (2X)		72 hrs @ 70° C	Substrate	Results	Status
			24 hrs @ 38° C / 95% RH	ABS	Good, Stable, no Lifting	Pass
			72 hrs @ -40° C			
	Specification: No Adhesion Loss or Delamination			Substrate	Results	Status
	2.2, Adhesion, Cycles (2X)		72 hrs @ 70° C	PP	Good, Stable, no Lifting	Pass
			24 hrs @ 38° C / 95% RH			
			72 hrs @ -40° C			
	Specification: No Adhesion Loss or Delamination			Substrate	Results	Status
	2.2, Adhesion, Cycles (2X)		72 hrs @ 70° C	E-COATED METAL	Good, Stable, no Lifting	Pass
			24 hrs @ 38° C / 95% RH			
			72 hrs @ -40° C			
	Specification: No Adhesion Loss or Delamination			Substrate	Results	Status
	2.2, Adhesion, Cycles (2X)		72 hrs @ 70° C	SS	Good, Stable, no Lifting	Pass
			24 hrs @ 38° C / 95% RH			
			72 hrs @ -40° C			

CERTIFIED BY:

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.