



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8397**
 SUPPORT: **NITRILE VINYL FOAM**
 SUBSTRATE: **E-COATED-METAL**
 CERT NO.: **230103 - 0841**



CHRYSLER MS-AY-522 B TYPE 1
 OEM Rev Date: Jul 06
 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
 Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 Heat Aging	Shrink	ASTM D3575-08*		
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	<u>Substrate</u> ABS		<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	<u>Substrate</u> PP		<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	<u>Substrate</u> E-COATED-METAL		<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
SECTION: 2.2 Adhesion				
Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	<u>Substrate</u> ABS		<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	<u>Substrate</u> PP		<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	<u>Substrate</u> E-COATED-METAL		<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass

CERTIFIED BY:

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.