

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FT B 12 PT BD NITRILE VINYL FOAM SS 230103 - 0848



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06 Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material Cellular PVN with PSA

TEST PARAMETERS: SEC

SECTION: 2.1 Heat Aging Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Shrink ASTM D3575-08* Substrate ABS	Results Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate PP	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate E-COATED METAL	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C	Substrate	<u>Results</u> Stable, Less than 5% Length and Width	<u>Status</u> Pass
SECTION: 2.2 Adhesion Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	e <mark>s or Delamiantion Substrate</mark> ABS	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> PP	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Los 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantion <u>Substrate</u> E-COATED METAL	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
Specification: No Adhesion Los 2.2, , Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	s or Delamiantior <u>Substrate</u> SS	<u>Results</u> Good, Stable, no Lifting	<u>Status</u> Pass
CERTIFIED BY:	44	ISSUE DATE: <u>1-1-24</u>	

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

> Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: 5-1-2005 Page 1 of 1