

**TEST REPORT** 

PRODUCT:

SUPPORT:

CERT NO .:

SUBSTRATE:

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com ANSI National Accreditation Board ACCREDITED

Results

**Results** 

Results

**TESTING LABORATORY** 

Status

**Pass** 

**Status** 

**Status** 

**Pass** 

Status

**CHRYSLER MS-AY-522 B TYPE 1** 

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

FT B 12 PT BD

**E-COATED METAL** 

**PET FOAM** 

230103 - 0848

Cellular PVN with PSA

**TEST PARAMETERS:** 

SECTION: 2.1 **Heat Aging** Shrink

> Specification: **Substrate**

Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C

ASTM D3575-08\*

Specification: **Substrate** 

2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass** 

Substrate Specification: < 5%

Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C E-COATED METAL

Specification: **Substrate Results** < 5%

2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width SS **Pass** 

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

**Results** 2.2, Adhesion, Cycles (2X) Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **ABS Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Results Substrate Status Good, Stable, no Lifting **Pass** 

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion** 

2.2, Adhesion, Cycles (2X) **Substrate** Results **Status** 72 hrs @ 70° C E-COATED METAL Good, Stable, no Lifting **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Cycles (2X) Results Substrate <u>Status</u> Good, Stable, no Lifting SS **Pass** 

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

**CERTIFIED BY:** 

1-1-24 ISSUE DATE:

Original Test Date:

Page 1 of 1

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.