

TEST REPORT

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

FT B EZ PRODUCT: SUPPORT: **EPDM FOAM** SUBSTRATE: **ABS** 230103 - 0848 CERT NO.:



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 **Heat Aging** Shrink ASTM D3575-08*

> Specification: **Substrate** Results Status Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **Pass**

> Specification: **Substrate Results Status** 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass**

> Substrate Specification: < 5% Results **Status**

> E-COATED METAL Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **Pass**

> Specification: **Substrate Results** < 5% Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width SS **Pass**

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

Results 2.2, Adhesion, Cycles (2X) Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **ABS Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion**

Substrate 2.2, Adhesion, Cycles (2X) Results **Status** 72 hrs @ 70° C E-COATED METAL Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

Dave Nichols Jr, Automotive Lab Technician

2.2, Cycles (2X) Substrate Results <u>Status</u> 72 hrs @ 70° C Good, Stable, no Lifting **Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

1-1-24 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

Original Test Date:

Page 1 of 1

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.