

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT PRODUCT: FT B EZ SUPPORT: **EPDM FOAM** SUBSTRATE: **E-COATED METAL**

230103 - 0848

ANSI National Accreditation Board ACCREDITED

Results

Results

TESTING LABORATORY

Status

Pass

Status

Status

CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

CERT NO.:

Shrink

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 **Heat Aging**

Specification:

Substrate 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width

ASTM D3575-08*

Specification: < 5% **Substrate**

2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass**

Specification: < 5% Substrate Results

E-COATED METAL Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **Pass**

Specification: **Substrate** Results < 5%

Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width SS **Pass**

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **ABS Pass**

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Substrate Results Status Good, Stable, no Lifting PP **Pass**

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion**

2.2, Adhesion, Cycles (2X) Substrate Results **Status** E-COATED METAL Good, Stable, no Lifting **Pass**

72 hrs @ 70° C 24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Cycles (2X) Substrate Results Status Good, Stable, no Lifting **Pass**

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

ISSUE DATE: 1-1-24

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date:

Page 1 of 1