

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

**TEST REPORT** 

FT B EZ PRODUCT: SUPPORT: **EPDM FOAM** 

SUBSTRATE:

230103 - 0848 CERT NO.:



**CHRYSLER MS-AY-522 B TYPE 1** 

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

**TEST PARAMETERS:** 

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

SECTION: 2.1 **Heat Aging** Shrink ASTM D3575-08\*

> Specification: **Substrate** Results Status Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C ABS **Pass**

> Specification: **Substrate Results Status** 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width **Pass**

> Specification: < 5% **Substrate** Results **Status**

> Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C E-COATED METAL **Pass**

> Specification: **Substrate Results** < 5% **Status** 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width SS **Pass**

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **ABS Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: **No Adhesion Loss or Delamiantion** 

2.2, Adhesion, Cycles (2X) **Substrate** Results **Status** 72 hrs @ 70° C E-COATED METAL Good, Stable, no Lifting **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Cycles (2X) **Substrate** Results <u>Status</u> 72 hrs @ 70° C Good, Stable, no Lifting SS **Pass** 

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Dave Nichols Jr, Automotive Lab Technician

**CERTIFIED BY:** 

1-1-24 ISSUE DATE:

Original Test Date:

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.