

**TEST PARAMETERS:** 

## **TEST REPORT**

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FT B EZ NITRILE VINYL FOAM PP 230103 - 0848



250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 email: psa.tape@averydennison.com URL: tapes.averydennison.com

## CHRYSLER MS-AY-522 B TYPE 1 OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material Cellular PVN with PSA

## SECTION: 2.1 Heat Aging Shrink ASTM D3575-08\* Specification: < 5% Substrate Results Status Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C ABS Pass Specification: < 5% **Substrate Results** Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width PP Pass Substrate Specification: < 5% Results Status Stable, Less than 5% Length and Width 2.1, Heat Aging, 30 mins @ 100° C **E-COATED METAL** Pass Specification: **Substrate Results** < 5% Status 2.1, Heat Aging, 30 mins @ 100° C Stable, Less than 5% Length and Width SS Pass SECTION: 2.2 Adhesion Specification: No Adhesion Loss or Delamiantion **Results** 2.2, Adhesion, Cycles (2X) Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting ABS Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C Specification: No Adhesion Loss or Delamiantion 2.2, Adhesion, Cycles (2X) Results Substrate Status 72 hrs @ 70° C Good, Stable, no Lifting PP Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C Specification: **No Adhesion Loss or Delamiantion** 2.2, Adhesion, Cycles (2X) **Substrate** Results Status 72 hrs @ 70° C E-COATED METAL Good, Stable, no Lifting Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C Specification: No Adhesion Loss or Delamiantior 2.2, , Cycles (2X) Results Substrate <u>Status</u> 72 hrs @ 70° C Good, Stable, no Lifting SS Pass 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C 1-1-24 CERTIFIED BY: **ISSUE DATE:** Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Page 1 of 1