

250 Chester Street

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

Painesville, Ohio 44077

email: psa.tape@averydennison.com

URL: tapes.averydennison.com **TEST REPORT**

PRODUCT: FT B

SUPPORT: NITRILE VINYL FOAM

SUBSTRATE: **ABS**

230103 - 0848 CERT NO.:

ANSI National Accreditation Board ACCREDITED

TESTING LABORATORY

CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material

Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1 **Heat Aging**

Specification:

2.1, Heat Aging, 30 mins @ 100° C

Specification: 2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5%

2.1, Heat Aging, 30 mins @ 100° C

Specification: < 5%

2.1, Heat Aging, 30 mins @ 100° C

Shrink ASTM D3575-08*

Substrate

Substrate

Substrate

E-COATED METAL

Substrate

SS

Substrate

ABS

Substrate

Substrate

E-COATED METAL

Substrate

Stable, Less than 5% Length and Width

Results Stable, Less than 5% Length and Width

Results

Status Pass

Status

Pass

Results **Status**

Stable, Less than 5% Length and Width **Pass**

Results

Results

Good, Stable, no Lifting

Stable, Less than 5% Length and Width

Status **Pass**

Status

Pass

Status

Pass

Status

Pass

Status

Pass

SECTION: 2.2 Adhesion

> Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification: No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X)

72 hrs @ 70° C 24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Specification:

Specification:

No Adhesion Loss or Delamiantion

2.2, Adhesion, Cycles (2X)

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH 72 hrs @ -40° C

No Adhesion Loss or Delamiantion

2.2, Cycles (2X)

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.