



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FBA 1960 12 PT BD**
 SUPPORT: **NITRILE VINYL FOAM**
 SUBSTRATE: **E-COATED METAL**
 CERT NO.: **230103 - 0944**



CHRYSLER MS-AY-545 B2
 OEM Rev Date: Oct 10
 Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
 B2 - with High Temp PSA


TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
3.0 Heat Resistance	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
3, Heat Resistance, Type 1 Adhesive Cycles (2X)			
72 hrs @ 70° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION:	Specification	Results	Status
3.0 Heat Resistance	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
3, Heat Resistance, Type 2 Adhesive Cycles (2X)			
72 hrs @ 79° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION:	Specification	Results	Status
3.4 Adhesion Test	0.9 N / cm	4.1	Pass
3.4, Adhesion Test, 20 mins @ RT			
ASTM D903-98 10			

SECTION:	Specification	Results	Status
3.6 Flammability	100 mm / minute	EBRTZ	Pass
3.6, Flammability, Initial, As Component			
FMVSS 302 09			

CERTIFIED BY: 
 Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.