



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **stus.averydennison.com**

**TEST REPORT**

PRODUCT: **FBR 1950**  
SUPPORT: **NITRILE VINYL FOAM**  
SUBSTRATE: **ABS**  
STD CERT NO.: **230103 - 0944**



**CHRYSLER MS-AY-545 C1**  
OEM Rev Date: Oct 10  
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation  
C1 - with Room Temp PSA and backing


**TAPE REQUIREMENTS:**

<b>SECTION: 3.0 Heat Resistance</b>	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 1 Adhesive Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	<b>No Adhesion Loss or Delamination</b>	Good, Stable, No Lifting	<b>Pass</b>

<b>SECTION: 3.0 Heat Resistance</b>	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 2 Adhesive Cycles (2X) 72 hrs @ 79° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	<b>No Adhesion Loss or Delamination</b>	Good, Stable, No Lifting	<b>Pass</b>

<b>SECTION: 3.4 Adhesion Test</b>	ASTM D903-98	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.4, Adhesion Test, 20 mins @ RT		<b>0.9 N / cm</b>	5.5	<b>Pass</b>

<b>SECTION: 3.6 Flammability</b>	FMVSS 302	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6, Flammability, Initial, As Component		<b>100 mm / minute</b>	< B 25	<b>Pass</b>

CERTIFIED BY:   
**Dave Nichols Jr, Automotive Lab Technician**

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.