



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **stus.averydennison.com**

TEST REPORT

PRODUCT: **FBR 1950**
 SUPPORT: **NITRILE VINYL FOAM**
 SUBSTRATE: **E-COATED METAL**
 STD CERT NO.: **230103 - 0944**



CHRYSLER MS-AY-545 C1
 OEM Rev Date: Oct 10
 Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
 C1 - with Room Temp PSA and backing


TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
3.0 Heat Resistance	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
3, Heat Resistance, Type 1 Adhesive Cycles (2X)			
72 hrs @ 70° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION:	Specification	Results	Status
3.0 Heat Resistance	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
3, Heat Resistance, Type 2 Adhesive Cycles (2X)			
72 hrs @ 79° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION:	Specification	Results	Status
3.4 Adhesion Test	0.9 N / cm	5.7	Pass
3.4, Adhesion Test, 20 mins @ RT			
ASTM D903-98			

SECTION:	Specification	Results	Status
3.6 Flammability	100 mm / minute	EBRTZ	Pass
3.6, Flammability, Initial, As Component			
FMVSS 302			

CERTIFIED BY: 
 Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.