



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: stus.averydennison.com

TEST REPORT

PRODUCT: FT 8327 12 PT BD
 SUPPORT: PET FOAM
 SUBSTRATE: E-COATED-METAL
 STD CERT NO.: 230103 - 0939



CHRYSLER MS-AY-545 C1
 OEM Rev Date: Feb 06
 Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
 C1 - with Room Temp PSA and backing

TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 1 Adhesive Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass

SECTION: 3.0 Heat Resistance	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3, Heat Resistance, Type 2 Adhesive Cycles (2X) 72 hrs @ 79° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass

SECTION: 3.4 Adhesion Test	ASTM D903-98	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.4, Adhesion Test, 20 mins @ RT		0.9 N / cm	10.1	Pass

SECTION: 3.6 Flammability	FMVSS 302	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6, Flammability, Initial, As Component		100 mm / minute	EBRZT	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.