

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1115 SUPPORT: **PORON FOAM**

SUBSTRATE: PP

230103 - 0948 CERT NO .:

CHRYSLER MS-CC-235

OEM Rev Date: Oct 04

Adhesion - PSA, Low Density Foam Sealing Applications

B - Supported Adhesive for Die Cut Parts



ACCREDITED TESTING LABORATORY

TEST PARAMETERS:

SECTION: **Adhesion**

Specification: No adhesion loss or lift 2.2 (A), Adhesion, 24 hrs @ RT	CLP-463TB-3-01A*	Results Good, stable, no lifting	Status Pass
Specification: No adhesion loss or lift 2.2 (B), Adhesion, 250 hrs @ 79°C	CLP-463CB-10-01*	Good, stable, no lifting	Pass
Specification: No adhesion loss or lift 2.2 (C), Adhesion, 250 hrs @ 38°C / 100% RH	ASTN D1735	Good, stable, no lifting	Pass
Specification: No adhesion loss or lift 2.2 (D), Adhesion, Cycles (3x)	CLP-463CB-10-01*	Good, stable, no lifting	Pass

Cycles (3x) 72 hrs @ 70°C

24 hrs @ 38° C / 95% RH

72 hrs @ -40°C

SECTION: 3.0 Adhesion

3.1, Adhesion, 24 hrs @ RT	CLP-4631B-3-01A*	<u>Results</u> 5.98	Status Pass
Specification: 3.2, Adhesion, 250 hrs @ 79°C	CLP-463CB-10-01*	15.49	Pass
Specification: 3.3, Adhesion, 250 hrs @ 38°C / 100% RH	ASTN D1735	12.43	Pass
Specification: 3.4, Adhesion, Cycles (3x)	CLP-463CB-10-01*	15.39	Pass

Cycles (3x) 72 hrs @ 70°C 24 hrs @ 38° C / 95% RH 72 hrs @ -40°C

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24 Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Ori

Original Test Date: 8-1-2007 Page 1 of 1