

TEST PARAMETERS:

250 Chester StreetPainesville, Ohio 44077Phone:866-GO-AVERY (866-462-8379)Fax:888-358-4469email:psa.tape@averydennison.comURL:tapes.averydennison.com

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.: **FT 1143** PORON FOAM PP 230103 - 0948



CHRYSLER MS-CC-235

OEM Rev Date: Oct 04 Adhesion - PSA, Low Density Foam Sealing Applications B - Supported Adhesive for Die Cut Parts

: Adhesio	n			
		CLP-463TB-3-01A*	<u>Results</u>	<u>Status</u>
2.2 (A), Adhesion	,24 hrs @ RT		Good, stable, no lifting	Pass
Specification:	No adhesion loss or lift	CLP-463CB-10-01*		
2.2 (B), Adhesion	, 250 hrs @ 79⁰C		Good, stable, no lifting	Pass
Specification:	No adhesion loss or lift	ASTN D1735		
2.2 (C), Adhesion	,250 hrs @ 38ºC / 100% RH		Good, stable, no lifting	Pass
Specification:	No adhesion loss or lift	CLP-463CB-10-01*		
2.2 (D), Adhesion	, Cycles (3x)		Good, stable, no lifting	Pass
	Specification: 2.2 (A), Adhesion Specification: 2.2 (B), Adhesion Specification: 2.2 (C), Adhesion Specification:	Specification:No adhesion loss or lift2.2 (A), Adhesion, 24 hrs @ RTSpecification:No adhesion loss or lift2.2 (B), Adhesion, 250 hrs @ 79°CSpecification:No adhesion loss or lift2.2 (C), Adhesion, 250 hrs @ 38°C / 100% RH	Specification:No adhesion loss or liftCLP-463TB-3-01A*2.2 (A), Adhesion, 24 hrs @ RTCLP-463CB-10-01*Specification:No adhesion loss or liftCLP-463CB-10-01*2.2 (B), Adhesion, 250 hrs @ 79°CSpecification:No adhesion loss or liftSpecification:No adhesion loss or liftASTN D17352.2 (C), Adhesion, 250 hrs @ 38°C / 100% RHSpecification:No adhesion loss or liftSpecification:No adhesion loss or liftCLP-463CB-10-01*	Specification:No adhesion loss or lift 2.2 (A), Adhesion, 24 hrs @ RTCLP-463TB-3-01A*Results Good, stable, no liftingSpecification:No adhesion loss or lift 2.2 (B), Adhesion, 250 hrs @ 79°CCLP-463CB-10-01*Good, stable, no liftingSpecification:No adhesion loss or lift 2.2 (C), Adhesion, 250 hrs @ 38°C / 100% RHASTN D1735Good, stable, no liftingSpecification:No adhesion loss or lift 2.2 (C), Adhesion, 250 hrs @ 38°C / 100% RHCLP-463CB-10-01*Good, stable, no lifting

Cycles (3x) 72 hrs @ 70°C 24 hrs @ 38° C / 95% RH 72 hrs @ -40°C

0 Adhesion becification: 1, Adhesion, 24 h	4.40 nrs @ RT	N / cm	CLP-463TB-3-01A*	Results 5.40	<u>Status</u> Pass
pecification: 2, Adhesion, 250	hrs @ 79ºC		CLP-463CB-10-01*	12.98	Pass
pecification: 3, Adhesion, 250	hrs @ 38ºC / 100	9% RH	ASTN D1735	12.66	Pass
pecification: 4, Adhesion, Cyc	les (3x)		CLP-463CB-10-01*	15.00	Pass

Cycles (3x) 72 hrs @ 70°C 24 hrs @ 38° C / 95% RH 72 hrs @ -40°C

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *. Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 8-1-2007 Page 1 of 1