



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FM 2455
SUPPORT: 2 MIL FOIL
SUBSTRATE: GLASS
CERT NO.: 230103 - 0948



CHRYSLER MS-CC-235
OEM Rev Date: Oct 10
Adhesion - PSA, Low Density Foam Sealing Applications
B - Supported Adhesive for Die Cut Parts

TAPE REQUIREMENTS:

SECTION: 2.2 (A) Adhesion
2.2 (A), Adhesion, 24 hrs @ RT

Specification
No Adhesion Loss or Lifting

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 2.2 (B) Adhesion
2.2 (A), Adhesion, 250 hrs @ 79°C

Specification
No Adhesion Loss or Lifting

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 2.2 (C) Adhesion
2.2 (A), Adhesion, 250 hrs @ 38°C / 100% RH

Specification
No Adhesion Loss or Lifting

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 2.2 (D) Adhesion
2.2 (A), Adhesion, Cycles (3x)
72 hrs @ 79°C
24 hrs @ 38°C / 95% RH
72 hrs @ -40°C

Specification
No Adhesion Loss or Lifting

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 3.0 (A)
3.0 (A), , 24 hrs @ RT

Specification
4.4 N / cm

Results
17.6

Status
Pass

SECTION: 3.0 (B)
3.0 (A), , 250 hrs @ 79°C

Specification
4.4 N / cm

Results
18.6

Status
Pass

SECTION: 3.0 (C)
3.0 (A), , 250 hrs @ 38°C / 100% RH

Specification
4.4 N / cm

Results
10.2

Status
Pass

SECTION: 3.0 (D)
3.0 (A), , Cycles (3x)
72 hrs @ 79°C
24 hrs @ 38°C / 95% RH
72 hrs @ -40°C

Specification
4.4 N / cm

Results
9.7

Status
Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.