



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 1115**  
 SUPPORT: **PORON FOAM**  
 SUBSTRATE: **ABS**  
 CERT NO.: **230105 - 1209**



**CHRYSLER MS-CC255**  
 OEM Rev Date: Oct 04  
 Adhesion - PSA, Low Density Foam Sealing Applications

**TEST PARAMETERS:**

**SECTION: 3.0 (A) Adhesion**

Specification:	Reference	Results	Status
<b>No adhesion loss or lift</b> 3.0 (A), Adhesion, 24 hrs @ RT	CLP 463TB-3-01A*	Good, stable, no lifting	<b>Pass</b>
<b>No adhesion loss or lift</b> 3.0 (B), Adhesion, 250 hrs @ 79°C	CLP 463TB-10-01*	Good, stable, no lifting	<b>Pass</b>
<b>No adhesion loss or lift</b> 3.0 (C), Adhesion, 250 hrs @ 38°C / 100% RH	ASTM D1735	Good, stable, no lifting	<b>Pass</b>
<b>No adhesion loss or lift</b> 3.0 (D), Adhesion, Cycles (3x)	CLP 463CB-10-01*	Good, stable, no lifting	<b>Pass</b>

Cycles (3x)  
 24 hrs @ 79°C  
 24 hrs @ 38° C / 95% RH  
 24 hrs @ -29°C

**SECTION: 4.0 180 Degree Peel Test**

Specification:	Reference	Results	Status
<b>0.45</b> N / mm 4.0 (A), 180 Degree Peel Test, 24 hrs @ RT	CLP 463TB-3-01A*	0.60	<b>Pass</b>
<b>0.30</b> 4.0 (B), 180 Degree Peel Test, 250 hrs @ 79°C	CLP 463TB-10-01*	1.55	<b>Pass</b>
<b>0.90</b> 4.0 (C), 180 Degree Peel Test, 250 hrs @ 38°C / 100% RH	ASTM D1735	1.24	<b>Pass</b>
<b>0.27</b> 4.0 (D), 180 Degree Peel Test, Cycles (3x)	CLP 463CB-10-01*	1.54	<b>Pass</b>

Cycles (3x)  
 24 hrs @ 79°C  
 24 hrs @ 38° C / 95% RH  
 24 hrs @ -29°C

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.  
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.