



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1143
SUPPORT: PORON FOAM
SUBSTRATE: ABS
CERT NO.: 230103 - 0948

CHRYSLER MS-CC255
OEM Rev Date: Oct 04
Adhesion - PSA, Low Density Foam Sealing Applications

TEST PARAMETERS:

SECTION: 3.0 (A) Adhesion

Table with 4 columns: Specification, Reference, Results, Status. Contains 4 rows of adhesion test data (3.0 A, B, C, D) with results like 'Good, stable, no lifting' and 'Pass'.

Cycles (3x)
24 hrs @ 79°C
24 hrs @ 38° C / 95% RH
24 hrs @ -29°C

SECTION: 4.0 180 Degree Peel Test

Table with 4 columns: Specification, Reference, Results, Status. Contains 4 rows of peel test data (4.0 A, B, C, D) with results like '0.54' and 'Pass'.

Cycles (3x)
24 hrs @ 79°C
24 hrs @ 38° C / 95% RH
24 hrs @ -29°C

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.