

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

6.3, Peel Adhesion, B. Initial @ RT

## **TEST REPORT**

PRODUCT: FT 1123

SUPPORT: 10 MIL CLEAR UHMWPE

SUBSTRATE: **E-COATED-METAL** CERT NO.: 230103 - 0949

CHRYSLER MS-CH-612

OEM Rev Date: Oct 04

Adhesive Rquirements, Pressure Sensitive Adhesive

Low Friction



**TEST PARAMETERS:** 

CLP 463TB-4-01\* **Specification** SECTION: 6.3 **Tensile Strength** Results **Status** 6.3, Tensile Strength, A. Initial @ RT 97.6 **Pass** 

35 N / cm

SECTION: 6.3 **Peel Adhesion Specification** CLP 463TB-3-01\* Results **Status** 

3.5 N/cm

4.6 **Pass** 

SECTION: 6.3 **Peel Adhesion** CLP 463CB-10-01\* **Specification** Results **Status Pass** 

3.5 N/cm 6.3, Peel Adhesion, B. 168 hrs @ 79° C

10.8

ISSUE DATE:

Original Test Date:

1-1-24

Page 1 of 1

1-18-2016

SECTION: 6.3 **Peel Adhesion ASTM D1735 Specification** Results **Status Pass** 

3.5 N/cm 6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH 9.1

SECTION: 6.3 **Peel Adhesion** CLP 463CB-10-01\* **Specification Results Status** 3.5 N/cm 9.6 **Pass** 

6.3, Peel Adhesion, B. Cycles (2X)

**CERTIFIED BY:** 

24 hrs @ 79° C 24 hrs @ 38° C / 95% RH

24 hrs @ -29° C

SECTION: 6.3 **Specification Shear Adhesion** CLP 463TB-8-01\* Results **Status** 

6.3, Shear Adhesion, C. Initial @ RT 104 kPa 261.6 **Pass** 

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.