



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126
SUPPORT: UHMWPE
SUBSTRATE: ABS
CERT NO.: 230103 - 0949



CHRYSLER MS-CH-612
OEM Rev Date: Oct 04
Adhesive Rquirements, Pressure Sensitive Adhesive
Low Friction

TEST PARAMETERS:

SECTION:	Test Description	Reference	Specification	Results	Status
6.3	Tensile Strength 6.3, Tensile Strength, A. Initial @ RT	CLP 463TB-4-01*	35 N / cm	53.1	Pass
6.3	Peel Adhesion 6.3, Peel Adhesion, B. Initial @ RT	CLP 463TB-3-01*	3.5 N / cm	13.2	Pass
6.3	Peel Adhesion 6.3, Peel Adhesion, B. 168 hrs @ 79° C	CLP 463CB-10-01*	3.5 N / cm	7.2	Pass
6.3	Peel Adhesion 6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH	ASTM 1735	3.5 N / cm	17.5	Pass
6.3	Peel Adhesion 6.3, Peel Adhesion, B. Cycles (2X) 24 hrs @ 79° C 24 hrs @ 38° C / 95% RH 24 hrs @ -29° C	CLP 463CB-10-01*	3.5 N / cm	6.0	Pass
6.3	Shear Adhesion 6.3, Shear Adhesion, C. Initial @ RT	CLP 463TB-8-01*	104 kPa	267.3	Pass

CERTIFIED BY:
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.