TEST REPORT



250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

psa.tape@averydennison.com email:

URL: tapes.averydennison.com PRODUCT: FT 8392 SUPPORT: **PEU FOAM** SUBSTRATE: 40% MICA PP 230103 - 1012 CERT NO.:



DELPHI SD2-324

OEM Rev Date: May 08

Pressure Sensitive Adhesives for HVAC Sealing Applications

Classification Requirements 4.3 Permanent Bond Adhesive

SECTION: 3.3 Service Temperature 3.3.1, Permanent Bond, 96 hrs @ -40°C	Specification No Adhesion Loss or Separation	Results Good, Stable, No Lifting	Status Pass
3.3.1, High Temp Permanent Bond, 96 hrs @ 121°C	No Adhesion Loss or Separation	Good, Stable, No Lifting	Pass
SECTION: 3.4 Humidity 3.4, Humidity, 50 hrs @ 38°C / 95% RH	Specification No Adhesion Loss, Discoloration or Softening	<u>Results</u> Stable, No Lifting or Visible Change	Status Pass
SECTION: 3.5 Objectionable Odor 3.5, Service Temperature, 1 hr @ 93°C	Specification 2 or Less Rating	Results 2	Status Pass
3.5, Service Temperature, 1 hr @ 93°C, 1 hr @ RT	2 or Less Rating	1	Pass
SECTION: 3.6 Fogging, Oil Bath 3.6, 6 hrs @ 85°C, 21°C Cooling, 16 hrs @ RT	GM 9305P 92 Specification 60 Units	Results 89.7	Status Pass
SECTION: 3.7 Creep 3.7, Creep, Ambient, 3.5 hrs @ 23°C	Specification No Slip	Results No Slip	Status Pass
SECTION: 4.3 Peel Test 4.3.1.1 (A), Peel Test, As Bonded @ RT	GMW 14124 10 600 N / m	802.8	Pass
4.3.1.1 (B), Peel Test, 72 hrs @ 93°C	350 N/m	952.5	Pass
4.3.1.1 (C), Peel Test, 24 hrs @ -40°C	350 N/m	1120.6	Pass
4.3.1.1 (D), Peel Test, 48 hrs @ 38°C / 100% RH	350 N/m	1105.8	Pass
4.3.1.1 (E), Peel Test, 800 hrs @ 93°C	350 N/m	728.4	Pass
SECTION: 4.3 Static Shear 4.3.1.2, Static Shear, Ambient, 3.5 hrs @ 23°C	No Slip	Results No Slip	Status Pass
SECTION: 4.3 Tensile Elongation * 4.3.1.3, Static Shear, Tensile, PET Only	ASTM D882-10* 1750 N / m	<u>Results</u> 2801.6	Status Pass
4.3.1.3, Static Shear, Elongation, PET Only	60 %	121.7	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24