



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FM 2454
SUPPORT: PET
SUBSTRATE: ABS
CERT NO.: 230103 - 0950



FCA MS-AY-512-B
OEM Rev Date : Nov 15
Polyethylene - Cellular - Water and Dust Seals
B - Cellular PE with PSA

TAPE REQUIREMENTS:

SECTION: 5.0 Flammability
5, Flammability
FMVSS 302
Specification < 100 mm / min
Results < B 17
Status Pass

SECTION: 6.0 Adhesion
6, Adhesion, Initial, Room Temp
ASTM D903
Specification > 274 N / m
Results 748.4
Status Pass

SECTION: 6.0 Adhesion
7, Adhesion, Environment Cycle (2x)
72 hrs @ 70°C
24 hrs @ 38°C / 95% RH
24 hrs @ -40°C
ASTM D903
Specification > 274 N / m
Results 542.9
Status Pass

SECTION: 7.0 Adhesion
3.2, Adhesion, Environment Cycle (2x)
72 hrs @ 70°C
24 hrs @ 38°C / 95% RH
24 hrs @ -40°C
ASTM D903
Specification No Adhesion Separation
Results No Lifting or Adhesion Loss
Status Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.