



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FM 2454**
SUPPORT: **PET**
SUBSTRATE: **GLASS**
CERT NO.: **230103 - 0950**



FCA MS-AY-512-B
OEM Rev Date : Nov 15
Polyethylene - Cellular - Water and Dust Seals
B - Cellular PE with PSA

TAPE REQUIREMENTS:

SECTION: 5.0 Flammability	FMVSS 302	<u>Specification</u>	<u>Results</u>	<u>Status</u>
5, Flammability		< 100 mm / min	EBRZT	Pass

SECTION: 6.0 Adhesion	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
6, Adhesion, Initial, Room Temp		> 274 N / m	1449.5	Pass

SECTION: 6.0 Adhesion	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
7, Adhesion, Environment Cycle (2x)		> 274 N / m	1299.5	Pass
72 hrs @ 70°C				
24 hrs @ 38°C / 95% RH				
24 hrs @ -40°C				

SECTION: 7.0 Adhesion	ASTM D903	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.2, Adhesion, Environment Cycle (2x)		No Adhesion Separation	No Lifting or Adhesion Loss	Pass
72 hrs @ 70°C				
24 hrs @ 38°C / 95% RH				
24 hrs @ -40°C				

CERTIFIED BY: 
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.