

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1115

SUPPORT: FOAM BACKED VINYL

SUBSTRATE: ABS

230103 - 0950 CERT NO .:



OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid

ACCREDITED

TESTING LABORATORY

109.4

101.3

Pass

Pass

substrate with the application of pressure.

TEST PARAMETERS:

Adhesive Peel Strength Specification Results SECTION: 3.2 Status 5.9 Initial, 24 hrs @ RT 2.7 N/cm **Pass**

Adhesive Peel Strength SECTION: 3.2 LP-463CB-10-01 Specification Results Status 6.3 1.8 N/cm **Pass** 168 hrs @ 79°C

SECTION: 3.2 **Adhesive Peel Strength Specification Status** ASTM D17363CB-10-01 **Results** 168 hrs @ 38°C / 98% RH 8.3 2.2 N/cm **Pass**

SECTION: 3.2 **Specification Adhesive Peel Strength Results** LP-463CB-10-01 Status 2.2 N/cm 7.8 **Pass**

Cycles, 3X

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

SECTION: 3,3 **Shear Adhesion Specification** Results **Status** Initial, 24 hrs @ RT 55 kPa 108.1 **Pass**

SECTION: 3,3 **Shear Adhesion** I P-463CB-10-01 **Specification** Results **Status** 168 hrs @ 79°C 117.4 **Pass** 48 kPa

Shear Adhesion SECTION: 3,3 **ASTM D1735 Specification** Results **Status**

55 kPa

55 kPa

SECTION: 3.3 **Shear Adhesion** LP-463CB-10-01 **Specification** Results Status

Cycles, 3X

24 hrs @ 79°C

168 hrs @ 38°C / 98% RH

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

CERTIFIED BY: ISSUE DATE: 1-1-24

Dave Nichols Jr. Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.